

Shiming Zhang

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/4771004/publications.pdf>

Version: 2024-02-01

22
papers

1,547
citations

430874

18
h-index

677142

22
g-index

23
all docs

23
docs citations

23
times ranked

2732
citing authors

#	ARTICLE	IF	CITATIONS
1	Biosensing Platform Based on Fluorescence Resonance Energy Transfer from Upconverting Nanocrystals to Graphene Oxide. <i>Angewandte Chemie - International Edition</i> , 2011, 50, 6851-6854.	13.8	277
2	Highly Fluorescent Polyimide Covalent Organic Nanosheets as Sensing Probes for the Detection of 2,4,6-Trinitrophenol. <i>ACS Applied Materials & Interfaces</i> , 2017, 9, 13415-13421.	8.0	234
3	Metal and Metal Oxide Interactions and Their Catalytic Consequences for Oxygen Reduction Reaction. <i>Journal of the American Chemical Society</i> , 2017, 139, 7893-7903.	13.7	135
4	Advanced Noncarbon Materials as Catalyst Supports and Non-noble Electrocatalysts for Fuel Cells and Metal-Air Batteries. <i>Electrochemical Energy Reviews</i> , 2021, 4, 336-381.	25.5	120
5	Fe-N doped carbon nanotube/graphene composite: facile synthesis and superior electrocatalytic activity. <i>Journal of Materials Chemistry A</i> , 2013, 1, 3302.	10.3	115
6	N-doped graphene/carbon composite as non-precious metal electrocatalyst for oxygen reduction reaction. <i>Electrochimica Acta</i> , 2012, 81, 313-320.	5.2	97
7	Pt utilization in proton exchange membrane fuel cells: structure impacting factors and mechanistic insights. <i>Chemical Society Reviews</i> , 2022, 51, 1529-1546.	38.1	80
8	Pyridinic-N Protected Synthesis of 3D Nitrogen-Doped Porous Carbon with Increased Mesoporous Defects for Oxygen Reduction. <i>Small</i> , 2019, 15, e1805325.	10.0	70
9	Tailoring molecular architectures of Fe phthalocyanine on nanocarbon supports for high oxygen reduction performance. <i>Journal of Materials Chemistry A</i> , 2015, 3, 10013-10019.	10.3	63
10	One-Pot Synthesized DNA-CdTe Quantum Dots Applied in a Biosensor for the Detection of Sequence-Specific Oligonucleotides. <i>Chemistry - A European Journal</i> , 2012, 18, 8296-8300.	3.3	51
11	Enhanced-electrocatalytic activity of Pt nanoparticles supported on nitrogen-doped carbon for the oxygen reduction reaction. <i>Journal of Power Sources</i> , 2013, 240, 60-65.	7.8	47
12	Synergistic increase of oxygen reduction favourable Fe-N coordination structures in a ternary hybrid of carbon nanospheres/carbon nanotubes/graphene sheets. <i>Physical Chemistry Chemical Physics</i> , 2013, 15, 18482.	2.8	42
13	Boosting the Performance of Iron-Phthalocyanine as Cathode Electrocatalyst for Alkaline Polymer Fuel Cells Through Edge-Closed Conjugation. <i>ACS Applied Materials & Interfaces</i> , 2018, 10, 28664-28671.	8.0	34
14	Sensitive monitoring and bioimaging intracellular highly reactive oxygen species based on gold nanoclusters@nanoscale metal-organic frameworks. <i>Analytica Chimica Acta</i> , 2019, 1092, 108-116.	5.4	33
15	High index surface-exposed and composition-graded PtCu ₃ @Pt ₃ Cu@Pt nanodendrites for high-performance oxygen reduction. <i>Chinese Journal of Catalysis</i> , 2021, 42, 1108-1116.	14.0	33
16	Nanoscaled luminescent terbium metal-organic frameworks for measuring and scavenging reactive oxygen species in living cells. <i>Journal of Materials Chemistry B</i> , 2019, 7, 3027-3033.	5.8	23
17	Induced growth of Fe-N x active sites using carbon templates. <i>Chinese Journal of Catalysis</i> , 2018, 39, 1427-1435.	14.0	22
18	Surfactant-Template Preparation of Polyaniline Semi-Tubes for Oxygen Reduction. <i>Catalysts</i> , 2015, 5, 1202-1210.	3.5	15

#	ARTICLE	IF	CITATIONS
19	Metathesis Reaction to Form Nanosheet-Structured Co(OH) ₂ Deposited on N-Doped Carbon as Composite Electrocatalysts for Oxygen Reduction. ACS Applied Energy Materials, 2021, 4, 4165-4172.	5.1	14
20	Synergy of staggered stacking confinement and microporous defect fixation for high-density atomic FeII-N4 oxygen reduction active sites. Chinese Journal of Catalysis, 2022, 43, 1870-1878.	14.0	9
21	Facile Synthesis of Surfactant-Induced Platinum Nanospheres with a Porous Network Structure for Highly Effective Oxygen Reduction Catalysis. Chemistry - an Asian Journal, 2022, 17, .	3.3	8
22	In-Situ Formed Micropores as Footholds Enabling Well-Dispersed High-Density Fe-Nx Active Sites for Oxygen Reduction Reaction. Journal of Physical Chemistry C, 0, , .	3.1	5